



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08G 18/54, 18/80	A1	(11) International Publication Number: WO 94/15984 (43) International Publication Date: 21 July 1994 (21.07.94)
(21) International Application Number: PCT/US94/00431 (22) International Filing Date: 12 January 1994 (12.01.94) (30) Priority Data: 08/002,391 12 January 1993 (12.01.93) US (71) Applicant: CYTEC TECHNOLOGY CORP. [US/US]; Suite 1300, 1105 North Market Street, Wilmington, DE 19801 (US). (72) Inventors: WU, Kuang, Jong; 15 Stonewall Lane, Shelton, CT 06484 (US). LEE, Feeha; 169 Osborne Hill Road, Fairfield, CT 06430 (US). (74) Agent: LERMAN, Bart, E.; Cytec Industries Inc., 1937 West Main Street, P.O. Box 60, Stamford, CT 06904-0060 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: ONE-PACKAGE POLYURETHANE TOP COAT COMPOSITION (57) Abstract A non-yellowing one-package polyurethane coating composition containing a blocked polyisocyanate, an isocyanate-reactive material, and an imino-functional amino resin is provided. The coating composition is applied onto an acid-cured base coat and cured. The clear coat produced in this manner has good yellowness resistance and intercoat adhesion. Articles such as multi-layered coated substrates are prepared using the coating method of this invention. The coated substrates typically contain an acid-cured first layer and an adjacent layer derived from a curable composition containing an oxime-blocked polyisocyanate, an isocyanate-reactive material, and an imino-functional amino resin.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

ONE-PACKAGE POLYURETHANE TOP COAT COMPOSITION

BACKGROUND OF THE INVENTION

5

Field of the Invention

This invention is an improvement in multi-layer coatings and methods of coating which utilize catalysts in one layer and blocked isocyanates in an adjacent layer.

10

Description of the Related Art

Modern automotive and appliance finishes are frequently two-layer coatings where a pigmented base coat is enhanced by covering with a clear top coat. In such multi-layer systems it is highly desirable that the top coat adhere strongly to the base coat and that the top coat not develop objectionable color.

15

Top coat color development and/or poor adhesion of the top coat to the base coat is a particular problem in two-layer coatings wherein one layer contains an acidic component and the adjacent layer contains a blocked isocyanate. This situation typically occurs where the base coat is crosslinked with amino resin type crosslinkers using acid catalysts and the top coat is a "one-package" polyurethane coating containing a blocked isocyanate wherein the blocking agent is released during heat curing. Surprisingly, it has been found that the addition of an amino resin with at least one imino-functional (-NH-) group to curable compositions which form polyurethane top coat layers adjacent acid-cured amino resin coating layers is highly beneficial for improvement of color and/or adhesion.

25

SUMMARY OF THE INVENTION

This invention is a curable composition comprising:

- (i) a blocked polyisocyanate;
- 30 (ii) an isocyanate-reactive material; and
- (iii) an imino-functional amino resin.

The curable composition is non-yellowing. When cured, it produces coatings with low yellowness, particularly when the coating is adjacent an acid-cured base coat.

This invention is also a method of coating substrates, comprising:

- (I) applying onto an acid-cured first coating layer, an adjacent coat of the curable composition of the invention; and thereafter
- 5 (II) curing said composition.

This invention is also a multi-layered coated substrate, comprising:

- (1) an acid-cured first layer; and
- (2) a cured polyurethane adjacent layer derived from the one-package polyurethane curable composition of the invention.

10

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

This invention is a curable one-package polyurethane composition containing a blocked polyisocyanate to which has been added an amino resin having at least one imino functionality. The composition is applied onto an acid-cured base coat to produce, after curing, a clear coat with low yellowness.

15

This invention is also a multi-layer coating method using the coating composition of the invention.

20

This invention is also a multi-layer coated article having adjacent layers wherein one layer has an acidic component and an adjacent layer has a blocked isocyanate wherein the blocking agent has been substantially released upon cure.

25

In the multi-layer coatings of this invention the polyurethane coating usually has the role of a clear top coat. However, in the broader context of this invention the polyurethane layer may be any coating stratum which is adjacent a coating layer containing one or more acidic components.

While this invention is not bound by any theory of operation, it is thought that the blocking agents released upon heat cure of the polyurethane coating layer react over a period of time with acidic components in adjacent layers to give poor interlayer adhesion and undesirable yellowing.

30

The polyurethane one-package coating composition of the invention comprises the following ingredients:

35

1. a blocked polyisocyanate
2. an isocyanate-reactive material, and
3. an imino-functional amino resin.

The Blocked Polyisocyanate Ingredient

In general, the blocked polyisocyanate ingredient is an adduct formed by adding a suitable blocking agent to some or all of the free isocyanate groups of a polyisocyanate, to thereby make the isocyanate groups inactive. When the adduct is heated to elevated temperatures, and/or put into contact with catalysts, the blocking agent readily dissociates from the isocyanate groups to regenerate free isocyanate groups. Such blocked polyisocyanates are already known. For example, they are described in Japanese Patent No. 91-068915.

The blocked polyisocyanate ingredient may be fully blocked (i.e., no free isocyanate groups remaining), or it may be a mixture of blocked and unblocked isocyanates, sometimes referred to herein as partially blocked isocyanates. The fully or partially blocked polyisocyanates usable in the improved one-package coating composition of the invention are further described below.

The coating composition of the invention contains either a blocked polyisocyanate whose isocyanate groups are blocked with an oxime, or a blocked polyurethane prepolymer whose terminal isocyanate groups are blocked with an oxime.

Any polyisocyanate is usable to form the partially or fully blocked polyisocyanate. Thus, the polyisocyanate may be, for example, an aromatic, aliphatic, aromatic-aliphatic or alicyclic polyisocyanate.

Typical aromatic polyisocyanates include 1,3-phenylene diisocyanate, 1,4-phenylene diisocyanate, 4,4'-diphenyldiisocyanate, 4,4'-diphenylmethane diisocyanate, 2,4-tolylene diisocyanate, 2,6 tolylene diisocyanate, 4,4'-toluidine diisocyanate, dianisidine diisocyanate, 4,4'-diphenylether diisocyanate, 4,4',4'-triphenylmethane triisocyanate, 1,3,5-trisocyanatobenzene and 2,4,6-trisocyanatotoluene. Typical aliphatic polyisocyanates include trimethylene diisocyanate, tetramethylene diisocyanate, hexamethylene diisocyanate, pentamethylene diisocyanate, 1,2-propylene diisocyanate, 2,3-butylene diisocyanate, 1,3-butylene diisocyanate, 2,4,4- or 2,2,4-trimethylhexamethylene diisocyanate and methyl 2,6-diisocyanatocaproate. Typical aromatic-aliphatic polyisocyanates include ω,ω' -diisocyanato-1,3-dimethylbenzene, ω,ω' -diisocyanato-1,4-dimethylbenzene, ω,ω' -diisocyanato-1,4-diethylbenzene, 1,3-tetramethylxylylene diisocyanate and 1,4-tetramethylxylylene diisocyanate. Typical alicyclic polyisocyanates include 1,3-cyclopentane diisocyanate, 1,4-cyclopentane diisocyanate, 1,4-cyclohexane diisocyanate, 1,3-cyclohexane diisocyanate, 3-isocyanatomethyl-3,5,5-trimethylcyclohexyl isocyanate, 4,4'-methylenebis-(cyclohexylisocyanate), methyl-2,4-cyclohexane diisocyanate, methyl-2,6-cyclohexane

diisocyanate, 1,4-bis(isocyanatomethyl) cyclohexane and 1,3-bis(isocyanatomethyl) cyclohexane. These polyisocyanates may be used singly or as a mixture.

Additionally, copolymers of isopropenyl-alpha, alpha-dimethylbenzyl isocyanate, particularly hydroxyethyl acrylate and methacrylate containing ω polymers thereof may be advantageously used to form the blocked polyisocyanate. Also usable are trimethylol propane adducts of the above-mentioned polyisocyanates as well as trimerized isocyanurate derivatives thereof. Polymeric polyisocyanates are also usable to form the blocked polyisocyanate, e.g., dimers or trimers of the diisocyanates as above-mentioned, polymethylene polyphenylene polyisocyanates, or modified derivatives such as with carbodiimide.

The polyurethane prepolymer used in the invention has terminal isocyanate groups in the molecule, and is obtained by the reaction of a polyisocyanate, such as those mentioned above with a polyhydric alcohol or a polyol, in amounts such that the isocyanate groups of the polyisocyanate are in molar excess to the number of hydroxyls of the polyhydric alcohol or polyol. The preferred isocyanate/hydroxyl equivalent ratios are about 1.2-5.0.

The polyol used has at least two reactive hydrogens in the molecule, and has a molecular weight preferably in the range of about 62 to about 100,000. The polyol used includes, for example, polyesterpolyols, polyetherpolyols, polyetheresterpolyols, polyesteramidopolyols, acrylic polyols, polyurethanepolyols, polycarbonatepolyols, epoxy polyols, epoxy-modified polyols, polyhydroxylalkanes, alkyd-modified polyols, castor oil, and mixtures of these.

The production of polyurethane prepolymers using polyols and polyisocyanates is well known in the art. By way of example, a polyol and a polyisocyanate are reacted usually at temperatures of about 0 to 200 °C, either in the presence or absence of a solvent. If desired, any known catalyst, such as tertiary amines, metal salts or organometallic compounds, is used.

A variety of polyesterpolyols are usable for the production of prepolymers, however, the reaction products of polyhydric alcohols and polybasic carboxylic acids are preferred. Preferred alcohols include diethylene glycol, ethylene glycol, neopentyl glycol, propylene glycol, trimethylolpropane, trimethylolethane and 2,2,4-trimethyl-1,3-pentanediol. Preferred acids include adipic acid, isophthalic acid, maleic anhydride, phthalic anhydride and terephthalic acid.

The oxime used as a blocking agent includes, for example, formaldoxime, acetaldoxime, acetoxime, methyl ethyl ketoxime, methyl isopropyl ketoxime, methyl butyl

The oxime used as a blocking agent includes, for example, formaldoxime, acetaldoxime, acetoxime, methyl ethyl ketoxime, methyl isopropyl ketoxime, methyl butyl ketoxime, diethyl ketoxime, diacetyl monooxime, cyclohexanone oxime, benzophenone oxime and the like. Mixtures of two or more of these oximes may be used, if necessary.

5 Among these oximes, methyl ethyl ketoxime and cyclohexanone oxime are particularly preferred.

The blocked polyisocyanate or polyurethane prepolymer used in the invention is obtained by reacting a polyisocyanate or a polyurethane prepolymer with a blocking agent in the conventional manner. The reaction may be carried out either in a solvent

10 which has no active hydrogen or in the absence of a solvent. The solvent having no active hydrogen is exemplified by esters such as ethyl acetate, butyl acetate, cellosolve acetate, carbitol acetate or dimethylesters of dibasic acids; ketones such as methyl ethyl ketone, methyl isobutyl ketone or cyclohexanone; and aromatic hydrocarbons such as toluene, xylene, Aromatic 100 or Aromatic 150 (the last two compounds, products of

15 Exxon Chemical, are aromatic solvents having 99.7% aromatics and 99.6% aromatics, respectively).

When necessary, a known catalyst may be used in the blocking reaction. Such catalysts include, for example, tertiary amines, and organotin compounds such as dibutyltin dilaurate, dibutyltin oxide, dibutyltin dichloride or tetrabutyl-1,3-

20 diacetoxydistannoxane. The reaction temperature is usually in the range of about 30 to 200 °C. After the polyisocyanate or prepolymer has been completely blocked, the blocked polyisocyanate or prepolymer may be diluted with a solvent having active hydrogen in the molecule.

25 The Isocyanate-Reactive Material

The isocyanate-reactive materials usable in the invention are polyfunctional active hydrogen-containing materials capable of bonding chemically to a polyisocyanate

The isocyanate-reactive material comprises at least one class of active hydrogen functionality selected from the group consisting of hydroxy, amino, mercapto (such as

30 thioglycerol), carboxy (such as polyacrylic acid or carboxy-functional polyesters), and a group convertible thereto. The hydroxy- and amino- functional groups are preferred.

Especially suitable isocyanate-reactive materials include hydroxy-functional polyesters, polyacrylates, and polyurethane prepolymers. The polyesters may be obtained in a known manner by, for example, the reaction of polycarboxylic acids with

35 excess quantities of polyhydric alcohols. The polyacrylates may be obtained by the

copolymerization of acrylic and methacrylic acid derivatives with hydroxy group-containing derivatives of these acids, such as, for example, hydroxyalkyl esters of acrylic and methacrylic acids, optionally with the simultaneous use of additional vinyl compounds, such as, for example, styrene. The hydroxy-functional polyurethane
5 prepolymers may be obtained in a known manner, by the reaction of polyisocyanates with excess quantities of compounds containing at least two hydroxy groups.

The amino-functional isocyanate-reactive material comprises compounds and resins selected from diamines such as ethylene diamine or hexamethylene diamine, from triamines such as diethylene triamine, tetramines such as triethylene tetramine,
10 polyamines such as polyallylamine, and mixtures thereof.

The Imino-Functional Amino Resin

Amino resins are polymers made by combining an aldehyde with a compound containing an amino group, and optionally thereafter etherifying with an alcohol, provided
15 that at least one imino-functional group, or a group convertible thereto, such as an N-methylol group, remains in the final product. The imino-functional amino resins prepared by this method may be monomeric or oligomeric, both of which are usable as the imino-functional amino resin ingredient of this invention. Examples of common imino-functional resins are those derived from melamines, guanamines, glycolurils, and ureas.
20 Melamine-derived amino resins are preferred.

The imino-functional amino resin found to have utility in the practice of this invention are ureaformaldehyde resins containing imino groups and those having imino groups pendent on nitrogen containing heterocyclic nuclei selected from the group consisting of melamine, oligomers of melamine, benzoguanamine, oligomers of
25 benzoguanamine, glycoluril, oligomers of glycoluril, cyclohexylcarboguanamine, oligomers of cyclohexylcarboguanamine, acetoguanamine, oligomers of acetoguanamine, dihydroxyethyleneurea, and mixtures thereof. The preferred imino-functional materials are those based on melamine and oligomers of melamine.

The imino-functional amino resin ingredient functions as a crosslinking agent and
30 also serves to inhibit the deleterious effects of highly acidic components that come into contact with the polyurethane.

The term "imino-functional" means an amino resin with an average -NH- content of about 3.0 weight percent, preferably from about 3.0 to about 35.7 weight percent, and more preferably from about 5.0 to about 25.0 weight percent, based on the weight of the
35 amino resin. It is recognized that suitable imino-functional amino resins are typically a

statistical distribution of resins of various degrees of substitution and molecular weight range. It is only necessary that in mixtures of resins the average imino content be in the range described. The imino content of the amino resin may be easily calculated if the chemical formula is known, or may be determined by titration. Accordingly, an amino resin is considered to have sufficient imino content if its calculated or determined "-NH-" content is within the above ranges.

An N-methylol functionality within the context of this invention is to be considered an "imino" functionality because under acid cure conditions it is convertible to an "NH" functionality by demethylation.

Examples of some imino-functional resins usable in this invention are partially methylated, partially butylated and mixed partially methylated/butylated resins such as CYMEL® 323 resin, CYMEL® 324 resin, CYMEL® 325 resin, CYMEL® 327 resin, CYMEL® 370 resin, CYMEL® 373 resin, CYMEL® 380 resin, CYMEL® 385 resin and CYMEL® 1158 resin. The CYMEL® resins are products of Cytec Industries Incorporated, West Paterson, New Jersey. The CYMEL® 323, 324, 325 and 327 resins are methoxymethyl-imino-functional and are partially methylolated and highly methylated. The CYMEL® 370, 373, 380 and 385 resins are methoxymethyl-methylol functional. The CYMEL® 1158 resin is butoxymethyl-imino-functional. The CYMEL® 1158 resin is butoxymethyl-imino-functional.

An example of a substantially methylolated, partially etherified, substantially oligomeric melamine is CYMEL® 370 resin.

An example of a partially methylolated but substantially fully etherified and substantially oligomeric melamine is CYMEL® 325 resin.

An example of a substantially monomeric imino-functional resin is CYMEL® 323. The formula that typifies CYMEL® 323 is substantially that of mono-N-methylol-N,N',N''-tri(methoxymethyl) melamine, wherein the N-methylol group is convertible to an "-NH-" group under the acidic conditions used to cure the compositions of the invention.

Optional Ingredients

In order to accelerate the crosslinking reaction between the blocked polyisocyanate and the isocyanate-reactive material, a cure catalyst may also be optionally used. However, the coating composition of the invention is capable of curing without the aid of an added catalyst. The cure catalysts usable are those widely used in polyurethanes and amino resins including bases such as 2,2,2-diazabicyclo-octane (DABCO), organometallic compounds, particularly organotin compounds such as

dibutyltin dilaurate, dimethyltin dilaurate, tetrabutyl diacetoxystannoxane (TBDAS), and acids such as p-toluene sulfonic acid.

Optional ingredients such as pigments, fillers, stabilizing additives, surface active agents, flow control agents may be additionally used to impart certain desirable properties to the coatings of this invention.

Proportions of Ingredients

The components of the one-package polyurethane composition of this invention are used in proportions well-known for such systems in the art. This typically requires that they be uniformly mixed so that the stoichiometric ratio of blocked isocyanate groups and isocyanate-reactive groups is in the range of about 1.2:1 to about 0.8:1, and preferably about 1:1.

The imino-functional amino resin is added in an amount sufficient to enhance adhesion and/or reduce yellowing when the composition forms a polyurethane coating over an acidic layer. Typically, from about 0.1 weight percent to about 30 weight percent (and preferably from about 5 weight percent to about 25 weight percent) of the imino-functional resin is added, based on the weight of all resin-forming ingredients in the polyurethane coating.

An imino-functional resin may be used as the sole crosslinker in the base coat. It may also be used in combination with a crosslinker which is free of any imino functionalities. CYMEL® 303 resin, a product of Cytec Industries Incorporated, West Paterson, New Jersey, is an example of a substantially fully alkoxymethylated amino resin substantially free of imino-functional groups. In the latter case, the ratio of the substantially fully alkoxymethylated amino resin to imino-functional amino resin is from about 19:1 to about 3:1.

Coating Method

The coating method of the invention comprises:

- (I) applying, onto a substrate, a one-package polyurethane coating composition, comprising:
 - (i) an oxime-blocked polyisocyanate;
 - (ii) an isocyanate-reactive material; and
 - (iii) an imino-functional amino resin; and thereafter
- (II) curing said one-package polyurethane coating composition.

The one-package polyurethane coating composition may additionally comprise a cure catalyst, such as an acid catalyst, to crosslink the imino-functional amino resin with an amino resin reactive material such as a hydroxy- or carboxy- functional acrylic or polyester resin and the like, or an organotin compound or a base to accelerate the polyurethane forming reactions.

To employ the method of the invention, a substrate is typically coated with multiple layers. For example, a layer containing highly acidic catalysts is adjacent a one-package polyurethane layer which contains a blocked isocyanate. The number or order of the applied layers is not critical. However, in conventional use a substrate of choice such as steel, plastic, or wood is first coated with an amino resin crosslinked base coat and cured. The base coat is thereafter topcoated with a one-package polyurethane coating composition (usually clear) and given a final cure. The coating method comprises using as the polyurethane top coat the novel polyurethane coating composition of the invention.

The base coat contains an acidic ingredient such as a strong acid catalyst and/or a resin containing carboxyl groups capable of acting as an acid catalyst. For the purposes of this invention, an acid catalyst is an acid with a pK_a of less than 5 and includes Lewis acids of any strength. Examples of acid catalysts are p-toluene sulfonic acid, dinonylnaphthalene disulfonic acid, dodecylbenzene sulfonic acid, oxalic acid, maleic acid, methyl p-tolyl sulfonimide, and latent forms thereof. Isocyanate-reactive polyol resins having acid numbers of at least one may in whole or in part replace common acid catalysts. Examples of such acidic resins are carboxy group-containing acrylic and polyester resins.

The acid-cured layer, which is the base coat, is typically derived from a substantially fully alkoxymethylated amino resin such as CYMEL® 303 resin, having the chemical name hexamethoxymethyl melamine. Other hexaalkoxymethyl melamines usable in the method of the invention have alkyl groups of 1 to 12 carbon atoms, including methyl, ethyl, 1-propyl, 2-propyl, 1-butyl, 2-butyl, iso-butyl, and mixtures thereof.

Alternatively, the acid-cured layer, which is the base coat, may be entirely derived from an imino-functional amino resin crosslinker. It may also be derived from a mixture of a substantially fully alkoxymethylated amino resin and any of the imino-functional amino resins.

The curable composition of the invention may be used, without a base coat, as a curable coating composition on a metal, wood, glass, or plastic substrate. It may also

be used for application, as a top coat, onto base coats which are cured under neutral conditions or are cured with an acid or a base. The preferred use of the curable composition, however, is its use as a polyurethane top coat for application onto an acid-cured base coat such as those derived from amino resins which are not imino-functional, such as CYMEL® 303 resin. Alternatively, it may be used on a base coat derived from an imino-functional amino resin such as CYMEL® 323, CYMEL® 324, CYMEL® 325, CYMEL® 327, CYMEL® 370, CYMEL® 373, CYMEL® 380, CYMEL® 385 and CYMEL® 1158, particularly in cases where the base coat is not acid-cured. Also particularly useful is the use of the curable composition of the invention as a polyurethane top coat applied over an acid-cured base coat derived from a mixture of a resin which is not imino-functional, such as CYMEL® 303 resin, and a resin which is imino-functional, such as CYMEL® 327 resin.

The preferred polyurethane top coat is a clear one-package oxime-blocked curable composition containing an imino-functional amino resin. More specifically, the coating method of the invention comprises:

- (a) applying onto a substrate, as a first coat, an acid-curable coating composition;
- (b) curing said curable coating composition to produce a first layer;
- (c) applying onto said first layer an adjacent coat of a one-package polyurethane coating composition, comprising:
 - (i) an oxime-blocked polyisocyanate;
 - (ii) an isocyanate-reactive material; and optionally
 - (iii) an imino-functional amino resin; and thereafter
- (d) curing said one-package polyurethane coating composition to produce a coated substrate having an acid-cured first layer and an oxime-blocked polyisocyanate derived adjacent layer;

with the proviso that at least one of the acid-cured first coat and the one-package adjacent polyurethane top coat contains an imino-functional amino resin.

In the practice of the method of the invention, a two-layered coating is prepared as follows. An acid-cured coating composition is first applied. Thereafter, a one-package oxime-blocked polyurethane coating composition is applied; however, before the application thereof, the first-applied acid-curable composition is fully or partially cured.

It is the discovery of this invention that yellowness resistance and intercoat adhesion of multi-layered coatings are improved by incorporating in a first acid-cured

layer, or in an adjacent oxime-blocked polyisocyanate derived layer, or in both the first and adjacent layers, an imino-functional amino resin to counter the deleterious effect of residual acids used for curing.

A significant aspect of this invention is exemplified when the first applied coating composition is partially cured before the oxime-blocked one-package polyurethane coating composition is applied. This approach is referred to herein as the "wet on wet" method of coating substrates. In this method of coating, yellowing is a more severe problem than it is in the "wet on dry" approach in which the base coat is first substantially fully cured. This is due to the greater facility of the residual acids to migrate from the base coat to an adjacent coat thereby causing severe yellowing in "wet on wet" systems.

In accordance with the method of this invention, the "wet on wet" yellowing problem is overcome by incorporating an imino-functional amino resin in the first layer, in the adjacent layer, or in both the first and adjacent layers of multi-layered coatings.

Coated Substrates

The practice of the method of the invention as set out in the preceding section produces a novel article which has a multi-layer coating that is highly resistant to yellowing and has improved adhesion.

EXAMPLE 1

The imino functionality of an imino-functional amino resin may be determined as follows:

Place 12 g of the imino-functional amino resin into a 100 ml beaker. Add 8 g of methanol. Dissolve the resin. Insert the electrodes of a pH meter, allowing about a minute for equilibrium to be established. With stirring, add Catalyst 1010 (i.e., a 10% solution of p-toluene sulfonic acid) from a burette placed above the beaker to lower the pH of the resin solution to 1.00 at 25°C. Calculate the imino content from the amount of acid used, by known methods.

EXAMPLE 2

Formulations A, B, C, D, and E were prepared as described in TABLE 2. Each formulation was applied to two white-basecoated Bonderite 100 (zinc phosphate-treated) cold roll steel (CRS) panels to produce two sets of five coated panels. The first set of five coated panels was thereafter heated in a vented oven at 125°C for 30 minutes and the second set was heated at 150°C also for 30 minutes. The physical and resistance

properties of the cured coatings produced in this manner are summarized in TABLE 1. The JONCRYL® 500 resin is an acrylic oligomer made by S.C. Johnson & Son, Inc., Racine, Wisconsin.

5 Coating A, which does not use any urethane as a crosslinking agent, exhibits the least amount of yellowing.

Coating B employs a fully alkoxymethylated melamine crosslinker such as CYMEL® 303 resin, in combination with an oxime-blocked polyisocyanate such as BI-12 blocked polyisocyanate crosslinker, also available from Cytec Industries Incorporated. BI-12 is an adduct of methyl ethyl ketone oxime-blocked meta-tetramethylxylylene diisocyanate and trimethylolpropane in a molar ratio of approximately 3:1. Coating B
10 exhibits the highest level of yellowing, particularly at the higher cure temperature of 150°C. Coating B illustrates the yellowing problem observed when CYMEL® 303 and an oxime-blocked polyisocyanate are used in combination.

Coatings C, D, and E illustrate the solution of the yellowing problem by
15 incorporating into the formulation an imino-functional amino resin such as CYMEL® 325 crosslinker in combination with BI-12 (Coating C), or DES B 3175 (Coating D), or IPDI B 1370 (Coating E). DES B 3175 is methyl ethyl ketone oxime-blocked tris-isocyanatohexyl isocyanurate, a product of Meyers Corporation. IPDI B 1370 is methyl
ethyl ketone oxime-blocked cycloaliphatic polyisocyanate, a product of Huels.

20 It is evident from the yellowing index of Coatings C, D, and E that incorporation of an imino-functional amino resin such as CYMEL® 325 provides an effective solution to the yellowing problem arising from the use of CYMEL® 303 and an oxime-blocked polyisocyanate in combination.

TABLE 1

ADDITION OF AN IMINO-FUNCTIONAL MELAMINE RESIN TO A ONE-PACKAGE
URETHANE TOP COAT* TO REDUCE YELLOWING

5	<u>FORMULATION**</u>	<u>A</u>	<u>B</u>	<u>C</u>	<u>D</u>	<u>E</u>
	JONCRYL® 500	65	65	65	65	65
	CYMEL® 303	--	20	--	--	--
	CYMEL® 325	35	--	20	20	20
	BI-12	--	15	15	--	--
10	DES B3175	--	--	--	15	--
	IPDI-B1370	--	--	--	--	15
	T-12 (Dibutyltindilaurate)	--	0.5	0.5	0.5	0.5
	pTSA (p-Toluenesulfonic acid)	0.4	0.4	0.4	0.4	0.4
15	<u>COATING PERFORMANCE</u>					
	<u>125°C/30 MIN.</u>					
	Film Thickness, mils	1.3	1.3	1.4	1.4	1.37
	Film Thickness, mm	0.033	0.033	0.036	0.036	0.035
	Hardness, KHN ₂₅	12.4	11.8	12.2	7.4	13.2
20	MEK Rubs	200+	75/200+	50/200+	145/175	50/200+
	Yellowing Index***	-4.2	+0.1	-3.3	-3.3	-3.5
	<u>150°C/30 MIN.</u>					
	Film Thickness, mils	1.2	1.3	1.3	1.3	1.3
25	Film Thickness, mm	0.033	0.033	0.033	0.033	0.033
	Hardness, KHN ₂₅	14.9	12.2	14.3	13.0	14.4
	MEK Rubs	200+	200+	200+	200+	200+
	Yellowing Index***	-4.11	+25.76	-2.47	-2.35	-3.19
30	* SUBSTRATE: Acid-cured white base coated Bondelite 100 CRS.					
	** To each formulation an organic coating solvent was added to produce a solution having a solids content of 50 weight percent. The solvent was a mixture of propylene glycol monomethyl ether acetate (PMA), methyl isobutyl ketone (MIBK) and xylene in a 50/50/20 mixture by weight.					
35	*** ASTM D 1638-74 method.					

EXAMPLE 3

The procedure of EXAMPLE 2 was repeated using the formulations described in TABLE 2. After curing, Formulations F and G produced the corresponding coatings. Coating F which contains an imino-functional amino resin and is produced by curing at 150 °C for 30 minutes has lower original yellowness and has lower increase in yellowness upon further heating under overbake conditions than coating G, which does not contain an imino-functional amino resin when subjected to the same cure/overbake conditions (TABLE 2). It is concluded, therefore, that the presence of an imino-functional amino resin such as CYMEL® 325 resin improves yellowing resistance of urethane top coats applied over an acid-cured base coat.

TABLE 2

ADDITION OF AN IMINO-FUNCTIONAL MELAMINE RESIN TO A
POLYURETHANE TOP COAT TO IMPROVE YELLOWING RESISTANCE

5

FORMULATION

Base coat: JONCRYL® 500/CYMEL® 303/TiO₂*/p-TSA**= 65/35/100/0.3

	Clear coat:	<u>F</u>	<u>G</u>
	JONCRYL® 500	53.3	53.3
10	BI-12	35.0	46.7
	CYMEL® 325 Resin	11.7	0.0
	T-12 (dibutyltin dilaurate)	0.5	0.5

Substrate: Bonderite 100 treated CRS (Cold Roll Steel)

15

CURE SCHEDULE

Base coat: 110°C for 20 minutes

Clear coat: 125°C for 30 minutes

150°C for 30 minutes

20

COATING PERFORMANCE

	Bake schedule	125°C/30 Min		150°C/30 Min	
	Clear coat	<u>F</u>	<u>G</u>	<u>F</u>	<u>G</u>
	Thickness, mils	1.8	1.8	1.9	1.8
	Thickness, mm	0.046	0.046	0.048	0.046
25	Hardness, KHN ₂₅	8.0	9.5	11.7	12.4
	Bake schedule	125°C/30 Min		150°C/30 Min	
	Clear coat	<u>A</u>	<u>B</u>	<u>A</u>	<u>B</u>
	Thickness, mils	1.8	1.8	1.9	1.8
30	Hardness, KHN ₂₅	8.0	9.5	11.7	12.4
	MEK rubs, mar	20	50	25	25
	remove	200+	200+	200+	200+
	Yellowness Index				
35	Original	-1.0	-0.7	2.6	9.3
	1st Overbake	-0.5	0.1	4.3	11.1
	2nd Overbake	-0.3	0.5	5.6	12.6
	3rd Overbake	0.0	1.1	7.0	14.2

40

- * Titanium dioxide pigment.
** para-toluene sulfonic acid.

EXAMPLE 4

The general procedure of EXAMPLE 2 was repeated using a self-crosslinking oxime-blocked polyisocyanate obtained by copolymerizing meta-isopropenyl-alpha, alpha dimethylbenzyl isocyanate (m-TMI) blocked with methyl ethyl ketone oxime (MEKO) and hydroxyethyl acrylate, butyl acrylate, and methyl methacrylate as the blocked polyisocyanate ingredient in the clear top coat formulation with (Formulation H) and without (Formulation I) the imino-functional amino resin CYMEL® 323.

The base coat formulation contained JONCRYL® 500 acrylic resin, CYMEL® 303 resin, titanium dioxide pigment and, as a cure catalyst, p-toluene sulfonic acid.

The base coat was applied to Bonderite 100 CRS panels, and cured at 110 °C for 30 minutes. Thereafter, each top coat formulation H and I, in an organic coatings solvent at 50% solids level, was applied to each base coated panel and cured at 125 °C for 30 minutes. The composition of the formulations H and I and the physical and resistance properties of the cured base coat/clear coat films are summarized in TABLE 4.

It is evident from the results of TABLE 3 that the presence of small amounts of an imino-functional amino resin such as CYMEL® 323 (Coating H) prevents yellowing. In contrast, the coating with no imino-functional resin present (Coating I) had unacceptable levels of yellowness upon cure.

TABLE 3

MEKO-BLOCKED TMI* SELF-CROSSLINKING COPOLYMERS
 ADDITION OF IMINO-FUNCTIONAL MELAMINE RESIN TO A
 URETHANE CLEAR TOP COAT TO IMPROVE YELLOWING RESISTANCE

5

FORMULATION	<u>H</u>	<u>I</u>
CLEAR COAT		
MEKO-TMI copolymer*	100.0	100.0
CYMEL® 323 resin	9.0	0.0
10 UL-28 (Dimethyltindilaurate)	0.5	0.5
BASE COAT		
JONCRYL® 500	65.0	65.0
CYMEL® 303 resin	35.0	35.0
TiO ₂ Pigment	100.0	100.0
15 PTSA (p-toluenesulfonic Acid)	0.3	0.3

CURE SCHEDULE

Base Coat: 110°C X 30 Min.

Clear Coat: 125°C X 30 Min.

20

COATING PERFORMANCE

Thickness, mils	1.5	1.5
Thickness, mm	0.038	0.038
Hardness, KHN ₂₅	10.3	10.1
25 MEK rubs	200+	200+
Yellowness Index		
Original	-0.5	2.3
1st Overbake (125°C X 30 Min)	0.4	4.6
2nd Overbake (125°C X 30 Min)	0.9	5.9

30

- * MEKO-TMI/HEA/BA/MMA/ = 15/20/30/35 (mole ratio); MEKO is methyl ethyl ketone oxime. TMI is meta-isopropenyl-alpha, alpha-dimethylbenzyl isocyanate, a product of Cytec Industries Incorporated, West Paterson, New Jersey, available under the tradename TMI®(meta) Unsaturated Aliphatic Isocyanate; HEA is hydroxyethyl acrylate;
- 35 BA is n-butyl acrylate; MMA is methylmethacrylate.

EXAMPLE 5

The procedure of EXAMPLE 2 was repeated to prepare coatings J and K using the corresponding formulations described in TABLE 4.

Coating performance and physical properties of the coatings are summarized in
5 TABLE 4.

It is evident from the results in TABLE 4 that replacing about 7.7 weight percent of CYMEL® 303 resin with an imino-functional CYMEL® 327 resin (Coating K) improves the intercoat adhesion (5 versus 0). It also improves the yellowness resistance by lowering the Yellowness Index of the coating (compare Yellowness Index of Coatings J
10 and K), particularly under overbake conditions.

TABLE 4
EFFECT OF ADDITION OF AN IMINO-FUNCTIONAL
AMINO RESIN TO THE BASE COAT

5	FORMULATION	<u>J</u>	<u>K</u>
	BASE COAT		
	JONCRYL® 500 acrylic resin	65	60
	CYMEL® 303 resin	35	35
	CYMEL® 327 resin	0	5
10	TiO ₂ Pigment	100	100
	pTSA (p-toluene sulfonic acid)	0.3	0.3
	TOP COAT		
	TA39-14*	56.3	56.3
	BI-12	43.7	43.7
15	UL-28 (Dimethyltin dilaurate)	0.5	0.5
CURE SCHEDULE			
	Base coat: 125 °C for 30 minutes		
	Top coat: 125 °C for 30 minutes		
20	COATING PERFORMANCE		
	Top Coat: Film Thickness, mils	1.6	1.6
	Film Thickness, mm	0.041	0.041
	Top Coat: Film Hardness, KHN ₂₅	9.3	9.4
25	Yellowness Index		
	Initial (125 °C X 30 Min)	0.1	-1.2
	1st Overbake (125 °C X 60 Min)	1.0	-0.6
	2nd Overbake (125 °C X 90 Min)	1.7	-0.6
	Intercoat Adhesion	0	5

30

* TA39-14 = a hydroxy-functional acrylic resin, a product of DOCK Resins, Inc.

EXAMPLE 6

The procedure of EXAMPLE 2 was repeated to prepare coatings L and M using the corresponding formulations (TABLE 5).

"Wet on wet" base coat/top coat systems were prepared as follows: each solvent-based formulation was applied onto CRS panels and the resulting base coated panels were allowed to dry at room temperature for about 30 minutes. The top coat was then applied onto the partially dried base coat without distorting the surface. This was accomplished by placing aluminum foil layers adjacent the partially dried base coat panels to hold the wire cator in a position just above the base coat during application of the top coat, thus permitting the preparation of a "wet on wet" base coat/top coat system without distorting the partially cured base coat.

The coating performance is summarized in TABLE 6.

It is concluded from TABLE 5 that:

- (a) base coats containing imino-functional resins such as CYMEL® 323 may be cured without the addition of external acids because small amounts of acid present in the acrylic component are sufficient to effect cure;
- (b) base coats containing imino-functional resins have better yellowing resistance than those having no imino-functional amino resins, particularly under "wet on wet" conditions.

TABLE 5

ADDITION OF AN IMINO-FUNCTIONAL MELAMINE RESIN TO THE BASE COAT TO
REDUCE YELLOWING

"WET ON WET" BASE COAT/URETHANE TOP COAT

5	FORMULATION	<u>L</u>	<u>M</u>
	BASE COAT:		
	ACRYLIC 145*	75	0
	QR 1295**	0	75
10	CYMEL® 323	25	0
	CYMEL® 303	0	25
	TiO ₂ Pigment	100	100
	DDBSA****		0.75
15	TOP COAT:		
	TA 39-14***	56	56
	BI 12	44	44
	UL-28 (Dimethyltin dilaurate)	0.5	0.5
20	CURE SCHEDULE		
	Wet on Wet, Baked at 125 °C/30 minutes.		
	COATING PERFORMANCE		
25	Thickness, mils	2.5	2.5
	Thickness, mm	0.064	0.064
	Hardness, KHN ₂₅	12.4	7.3
	MEK Rubs	200+	150/200+
	Yellowing Index		
	Original (125 °C X 30 Min)	-3.1	0.7
30	1st Overbake (125 °C X 60 Min)	-2.7	2.4
	2nd Overbake (125 °C X 90 Min)	-2.5	3.7
	3rd Overbake (125 °C X 120 Min)	-2.3	5.6
35	* Acrylic 145 =	a hydroxy-functional acrylic resin, prepared by American Cyanamid Co., Wayne, New Jersey. Acrylic 145 has an acid number of about 20.	
	** QR 1295 =	a hydroxy-functional acrylic resin, a product of Rohm and Haas Company.	
	*** TA 39-14 =	a hydroxy-functional acrylic resin, a product of DOCK Resins, Inc.	
40	**** DDBSA =	Dodecylbenzenesulfonic acid cure catalyst.	

Although the present invention has been described with reference to certain preferred embodiments, it is apparent that modifications and variations thereof may be made by those skilled in the art without departing from the scope of this invention as

5 defined by the appended claims.

WE CLAIM:

1. A curable composition comprising:
 - (i) a blocked polyisocyanate;
 - (ii) an isocyanate-reactive material; and
 - (iii) an imino-functional amino resin having an average -NH- content of about 3.0 percent by weight or higher.
2. A non-yellowing one-package coating composition comprising:
 - (i) an oxime-blocked polyisocyanate;
 - (ii) an isocyanate-reactive material; and
 - (iii) an amino resin having an average -NH- content of about 3.0 percent by weight or higher.
3. The composition of claim 2 wherein the oxime is selected from the group consisting of formaldoxime, acetaldoxime, acetone oxime, methyl ethyl ketone oxime, methyl isopropyl ketone oxime, methyl butyl ketone oxime, diethyl ketone oxime, diacetyl mono oxime, cyclohexanone oxime, benzophenone oxime, and a mixture thereof.
4. The composition of claim 2 wherein the polyisocyanate is selected from the group consisting of hexamethylene diisocyanate, 3-isocyanatomethyl-3,5,5-trimethylcyclohexyl isocyanate, m-isopropenyl-alpha, alpha-dimethylbenzyl isocyanate copolymers, 1,3-tetramethylxylylene diisocyanate, trimethylol propane adducts thereof, trimerized isocyanurate derivatives thereof, and a mixture of the preceding polyisocyanates.
5. The composition of claim 4 wherein the polyisocyanate is a self-crosslinking m-isopropenyl-alpha, alpha-dimethylbenzyl isocyanate copolymer comprising hydroxyethyl acrylate and methacrylate units.
6. The composition of claim 2 wherein the isocyanate-reactive material comprises at least one class of active hydrogen functionality selected from the group consisting of hydroxy, amino, mercapto, carboxy, and a group convertible thereto.

7. The composition of claim 2 wherein the imino-functional amino resin is derived from monomeric or oligomeric hydroxymethylated, alkoxymethylated, or a mixture of hydroxymethylated and alkoxymethylated amino resins selected from the group consisting of melamines, guanamines, glycolurils and ureas.
8. The composition of claim 2 wherein the average imino content in the imino-functional amino resin is in the range of from 3.0 to 35.7 weight percent.
9. The composition of claim 2 wherein the stoichiometric ratio of the blocked polyisocyanate groups and isocyanate-reactive groups is in the range of 1.2:1 to 0.8:1.
10. The composition of claim 2 wherein the imino-functional amino resin is present in an amount sufficient to reduce yellowing, enhance adhesion, or both.
11. The composition of claim 2 further comprising a cure catalyst selected from the group consisting of acids, bases, and organotin compounds.
12. A method of coating a substrate comprising the steps of:
 - (I) applying onto a substrate the one-package polyurethane coating composition as set forth in any one of claims 2-11; and thereafter
 - (II) curing said one-package polyurethane coating composition.
13. The method of claim 12 wherein the substrate has coated thereon, as a base coat, an acid-cured coating.
14. The method of claim 13 wherein the acid-cured base coat is prepared using a crosslinker selected from the group consisting of substantially fully alkoxymethylated amino resin, an imino-functional amino resin, and a mixture thereof.

15. A method of coating a substrate comprising the steps of:
- (a) applying, onto a substrate, as a first coat, an acid-curable coating composition;
 - (b) at least partially curing said acid-curable coating composition to produce a first layer;
 - (c) applying, onto said first layer an adjacent coat of a one-package polyurethane coating composition, comprising:
 - (i) an oxime-blocked polyisocyanate;
 - (ii) an isocyanate-reactive material; and optionally
 - (iii) an imino-functional amino resin; and thereafter
 - (d) curing said one-package polyurethane coating composition to produce a coated substrate having an acid-cured first layer and an oxime-blocked polyisocyanate-derived adjacent layer;
- with the proviso that at least one of the acid-curable first coat and one-package adjacent polyurethane top coat contains an imino-functional amino resin having an average -NH- content of about 3.0 percent by weight or higher.
16. The method of claim 15 wherein the acid-curable coating composition comprises, as a crosslinker, an amino resin selected from the group consisting of substantially fully alkoxymethylated amino resin, an imino-functional amino resin, and a mixture thereof.
17. The method of claim 16 wherein the substantially fully alkoxymethylated amino resin is hexaalkoxymethyl melamine wherein the alkyl group is selected from the group consisting of methyl, ethyl, 1-propyl, 2-propyl, 1-butyl, 2-butyl, iso-butyl, and a mixture thereof.
18. The method of claim 17 wherein the imino-functional amino resin of the crosslinker and the optional imino-functional amino resin, if present, are each selected from the group consisting of imino-functional melamines, guanamines, glycolurils, ureas and a mixture thereof.
19. The method of claim 15 wherein the imino-functional amino resin component (iii) is present.

20. The method of claim 19 wherein the imino-functional amino resin is selected from the group consisting of imino-functional melamines, guanamines, glycolurils, ureas, and a mixture thereof.
21. The method of claim 15 wherein the one-package polyurethane coating composition further comprises a cure catalyst.
22. The method of claim 21 wherein the cure catalyst is selected from the group consisting of an organotin compound, an acid, and a mixture thereof.
23. The method of claim 21 wherein the cure catalyst is selected from the group consisting of an organotin compound, a base, and a mixture thereof.
24. The method of claim 15 wherein the the one-package polyurethane coating composition is applied wet on wet onto said first layer.
25. A coated substrate prepared by the method of any one of claims 15-24.
26. A coated substrate comprising:
- (1) a first layer derived from an acid-curable coating composition; and
 - (2) a cured polyurethane adjacent layer derived from a one-package polyurethane curable composition, comprising:
 - (i) an oxime-blocked polyisocyanate;
 - (ii) an isocyanate-reactive material; and optionally
 - (iii) an imino-functional amino resin;
- with the proviso that at least one of the acid-curable coating composition and the one-package polyurethane curable composition contains an imino-functional amino resin having an average -NH- content of about 3.0 percent by weight or higher.

INTERNATIONAL SEARCH REPORT

Inter. nat. Application No.

PCT/US 94/00431

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 C08G18/54 C08G18/80

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB,A,2 254 328 (NIPPON PAINT) 7 October 1992 see page 3, line 17 - page 16, line 23; claims ---	1-3,6-26
X	FR,A,2 265 828 (CASSELLA FARBERWERKE) 24 October 1975 see page 2, line 1 - page 8, line 8; claim 1 ---	1
X	EP,A,0 410 365 (VIANOVA KUNSTHARZ) 30 January 1991 see page 2, line 23 - page 4, line 13; claim 1 --- -/--	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

11 May 1994

Date of mailing of the international search report

25.05.94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Bourgonje, A

INTERNATIONAL SEARCH REPORT

Inter: nal Application No

PCT/US 94/00431

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	EP,A,0 551 727 (MORTON INTERNATIONAL) 21 July 1993 see page 4, line 1 - page 5, line 16; claim 1	1-3
A	----- WO,A,92 07823 (ALLIED-SIGNAL) 14 May 1992 see the whole document -----	5

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter national Application No

PCT/US 94/00431

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
GB-A-2254328	07-10-92	JP-A-	4130168	01-05-92
		US-A-	5187199	16-02-93
FR-A-2265828	24-10-75	DE-A-	2414427	23-10-75
		AT-B-	338391	25-08-77
		BE-A-	827154	25-09-75
		CH-A-	598341	28-04-78
		GB-A-	1467103	16-03-77
		JP-A-	50135121	27-10-75
		NL-A-	7503337	30-09-75
		SE-A-	7503195	29-09-75
EP-A-0410365	30-01-91	US-A-	3954900	04-05-76
		AT-B-	392075	25-01-91
		CA-A-	2022101	29-01-91
		DE-D-	59005069	28-04-94
		JP-A-	3074477	29-03-91
EP-A-0551727	21-07-93	US-A-	5178915	12-01-93
		AU-B-	645222	06-01-94
		AU-A-	2835692	15-07-93
		CA-A-	2083235	11-07-93
WO-A-9207823	14-05-92	AU-A-	8908191	26-05-92